



INTERPARTNER



White Top Test Liner (WTTL) Recycled, Uncoated, Whiteness 65

Característica Típicas (Typical Values)

ENSAYO (TEST)	NORMA (STANDARDS)	UNIDADES (UNITS)					
Gramaje (Substance)	ISO 536	g/m^2	145	160	180	200	250
Humedad (Moisture)	ISO 287	%	7				
RCT¹	ISO 9895	kN/m	0,89	0,91	1,45	1,63	1,97
		$kN \cdot m/kg$	6,15	5,68	8,13	8,14	7,87
Resistencia al estallido (Burst)	ISO 2758	kPa	288	314	347	362	399
		$kPa \cdot m^2/g$	1,98	1,96	1,83	1,81	1,59
Scott Bond	TAPPI-833	J/m^2	282	268	233	222	225
		$lb \cdot 10^{-3}/ft$	134	128	111	106	107
Resistencia a la tracción (Tensile Stiffness)	ISO 1924	kN/m	5,23	7,17	7,04	8,20	8,30
Blancura (Whiteness)	ISO 2470-1	%	← 65 →				

Características garantizadas (Guaranteed values)

ENSAYO (TEST)	NORMA (STANDARDS)	UNIDADES (UNITS)					
Gramaje nominal (Grammage)	ISO 536	g/m^2	145	160	180	200	250
Gramaje medio (Average Grammage)			Nominal $\pm 3\%$				
Humedad nominal (Moisture)	ISO 287	%	7				
Humedad media (Nominal Moisture)			Nominal -1,5 +1				
RCT¹	ISO 9895	kN/m	0,67	0,82	1,27	1,38	1,85
		$kN \cdot m/kg$	4,65	5,13	6,34	6,89	7,39
Resistencia al estallido (Burst)	ISO 2758	kPa	277	283	345	356	392
		$kPa \cdot m^2/g$	1,91	1,77	1,91	1,78	1,57
Scott Bond	TAPPI-T833	J/m^2	235	226	222	216	219
		$lb \cdot 10^{-3}/ft$	112	108	106	103	104
Resistencia a la tracción¹ (Tensile Stiffness)	ISO 1924	kN/m	5,04	6,14	6,97	7,15	8,15
Blancura (Whiteness)	ISO 2470-1	%	← ≥ 60 →				

¹ Se expresa como el valor medio entre DT y DL (Expressed as the average value between CD and MD)

