

WHITE TOP LINER

TDS / Características Técnicas	Units / Unidades	Var.	WTL 125 g	WTL 130 g	WTL 140 g	WTL 175 g	WTL 235 g
Substance / Gramaje	g/m2	+/-3%	125 g	130 g	140 g	175 g	235 g
Humidity / Humedad	%	+/-1,5%	7%	7%	7%	7%	7%
Whitness / Blancura	Photovolt.		>65°	>65°	>65°	>65°	>65°
Mullen Index / Estallido	kpa.		>200	>200	>200	>280	>380
RCT.DT	KN/m		>0.75	>0.7	>0.7	>1.1	>1.6
Bond Tester	ft.lb		>130	>115	>115	>120	>120
COBB	g/m2		<40	<40	<40	<40	

In compliance with Norm UNE 57001 / ISO 187

En cumplimiento con la NORMA UNE 57001 / ISO 187

